

(12) **UK Patent Application** (19) **GB** (11) **2 302 367** (13) **A**

(43) Date of A Publication 15.01.1997

(21) Application No 9612834.3

(22) Date of Filing 17.06.1996

(30) Priority Data

(31) 07148649
9612207(32) 15.06.1995
11.06.1996(33) JP
GB

(71) Applicant(s)

Nippondenso Co Limited

(Incorporated in Japan)

1-1 Showa-Cho, Kariya-City, Aichi-Pref. 448, Japan

(72) Inventor(s)

Kenji Horibe
Hironori Osamura
Nobuo Abe
Keiji Kanao

(74) Agent and/or Address for Service

Withers & Rogers
4 Dyer's Buildings, Holborn, LONDON, EC1N 2JT,
United Kingdom(51) INT CL⁶**H01T 13/39, C22C 5/04**

(52) UK CL (Edition O)

F1B BCAD**C7A AB249 AB279 AB289 AB309 AB319 AB339 AB349**
AB369 AB389 AB39Y AB392 AB394 AB395 AB396
AB397 AB399 AB419 AB439 AB459 AB489 AB519
AB52Y AB537 AB539 AB549 AB55Y AB553 AB555
AB556 AB557 AB558 AB559 AB610 AB613 AB616
AB619 AB62X AB621 AB624 AB627 AB63X AB63Y
AB635 AB66X AB661 AB663 AB664 AB665 AB667
AB669 AB670 AB675 AB682 AB684 AB686 AB688
AB70X AB702 A71Y
U1S S2073

(56) Documents Cited


GB 0479540 A **JP 610044141 A**

(58) Field of Search

UK CL (Edition O) C7A, F1B BCAD
INT CL⁶ C22C 5/04, H01T 13/39
Online: EDOC, WPI(54) **I.c. engine spark plug with noble metal chip of Ir-Rh alloy**

(57) A noble metal chip 5, 6 is bonded to a discharging spot of the centre or ground electrode 3, 4 of the spark plug, the noble metal being an Ir-Rh alloy containing 1-60%, preferably 3-30%, by weight of Rh. The alloy may also contain 0.5 to 5 wt% of an oxide of an element of group 3A or 4A of the periodic table. The electrode may have a shell portion of a Ni alloy to which the chip is bonded by laser or resistance welding. The dimensions of the chips may be A: 0.5 to 2.0mm, B: 0.3 to 2.5 mm; C: 0.5 to 1.7 mm; D: 0.3 to 1.0 mm. The chip has improved heat resistance and lifetime at higher temperatures and allows reduction of the electrode diameter.

Fig. 2


**BEST AVAILABLE COPY**

At least one drawing originally filed was informal and the print reproduced here is taken from a later filed formal copy.

This print takes account of replacement documents submitted after the date of filing to enable the application to comply with the formal requirements of the Patents Rules 1995

1/3

Fig. 1



2/3

Fig. 2





Fig. 3



$\frac{3}{3}$

SPARK PLUG FOR INTERNAL COMBUSTION ENGINE

5

The present invention relates to a spark plug for an internal combustion engine and a noble metal chip for the electrodes of the spark plug.

10

With regard to spark plugs for internal combustion engines, it is a continuing need to improve the lifetime (i.e., to improve the consumption resistance) and the performance (i.e., to improve the spark flyability and the ignitability). To this end, attempts have been made to use a noble metal chip, particularly of Pt, as a discharging element of the spark plug for an internal combustion engine.

15

Recently, there is an increasing need to further improve the lifetime and the performance. To this end, studies have been conducted to use a noble metal chip made of Ir having a melting point higher than that of Pt.

20

Although Ir advantageously has a melting point of 2454°C , which is much higher than that of Pt, it also has a disadvantage that the volatilization consumption is undesirably accelerated at elevated temperatures above 900°C .

25

To suppress the volatilization consumption of Ir, Japanese Unexamined Patent Publication (Kokai) No. 2-186579 proposed introduction of Al, Y or other elements having a strong affinity for oxygen and precipitation thereof to form an oxidation-protection film over the surface of an Ir electrode, thereby preventing the volatilization consumption of Ir.

30

However, the proposal had a drawback that the oxidation-protection film is composed of alumina, yttria, or other ceramics, which provides poor bond with the Ir

35

noble metal and causes spalling thereof.

Japanese Unexamined Patent Publication (Kokai)
No. 2-49388 proposed addition of Pt to Ir, but could not
provide a satisfactory noble metal chip having a
sufficiently improved consumption resistance and heat
resistance at high temperatures.

An object of the present invention is to provide a
spark plug having a noble metal chip bonded to the
discharging spot thereof and having an improved heat
resistance and consumption resistance at high
temperatures.

Another object of the present invention is to
provide a noble metal chip for a spark plug, the chip
having an improved heat resistance and consumption
resistance at high temperatures.

To achieve the object according to the present
invention, a spark plug has a noble metal chip bonded to
the discharging spot thereof, the chip consisting of an
Ir-Rh alloy containing Rh in a specified amount to cause
enrichment and precipitation of Rh on the chip surface
and the precipitated Rh forms an oxidation-protection
film. Because Rh is a noble metal having a high melting
point and forming a strong bond with the chip body of the
Ir-Rh alloy, the oxidation-protection film of the present
invention provides an improved consumption resistance and
heat resistance at high temperatures.

The alloying of Ir with Rh advantageously provides a
noble metal chip having an improved consumption
resistance and heat resistance at high temperatures, so
that the noble metal chip of the present invention, when
used in the spark plug of an internal combustion engine,
allows reduction in the electrode diameter, and thereby
improves the performance of the spark plug for an
internal combustion engine, particularly a reduced
discharging voltage and an improved ignitability.

Figure 1 is a semi-cross-sectional view of a spark plug for an internal combustion engine according to the present invention;

Fig. 2 is an enlarged partial cross-sectional view of the spark plug shown in Fig. 1; and

Fig. 3 is a graph showing the consumptions of various chips as a function of the testing time.

According to the present invention, a spark plug for an internal combustion engine comprises:

an insulation porcelain (2) having a throughhole (2a);

a center electrode (3) held at one end of the throughhole (2a);

a housing (1) holding the insulation porcelain (2);

a ground electrode (4) disposed at an front end of the housing (1) and facing the center electrode (3);

a spark gap (7) defined by the center electrode (3) and the ground electrode (4); and

the center electrode (3) and/or the ground electrode (4) having a noble metal chip (5, 6) bonded to a discharging spot of an front end thereof, wherein the noble metal chip (5, 6) consisting of an Ir-Rh alloy contains Rh in an amount of from 1 wt% to 60 wt%, preferably from 3 wt% to 30 wt%.

The Ir-Rh alloy preferably further contains an oxide of an element of the group 3A or 4A of the periodic table in an amount of from 0.5 wt% to 5 wt%. The oxide of the element of the group 3A preferably consists of Y_2O_3 . The oxide of the element of the group 4A preferably consists of ZrO_2 .

In a preferred embodiment of the present invention, the center electrode has the noble metal chip having an outer diameter A and a height B which are within the range defined by the following formulae:

$0.5 \text{ mm} \leq A \leq 2.0 \text{ mm}$, and

$0.3 \text{ mm} \leq B \leq 2.5 \text{ mm}$.

In a more preferred embodiment of the present invention, the ground electrode has the noble metal chip
5 having an outer diameter C and a height D which are within the range defined by the following formulae:

$0.5 \text{ mm} \leq C \leq 1.7 \text{ mm}$, and

$0.3 \text{ mm} \leq D \leq 1.0 \text{ mm}$.

10 The center electrode and/or the ground electrode preferably have a shell portion composed of a Ni alloy and have the noble metal chip bonded to the discharging spot of the front end thereof by laser welding or resistance welding.

Examples

15 Figure 1 is a semi-cross-sectional view of a spark plug for an internal combustion engine according to the present invention. Figure 2 is a partial cross-sectional view showing the lower end portion of the plug shown in Fig. 1. The spark plug has a tubular housing 1 made of
20 iron or other metal and having a thread 1a on the outer circumferential surface at the lower portion.

A tubular insulation porcelain 2 is made of alumina or other insulating material and has a lower portion coaxially engaged in the housing 1 with the upper end 1b
25 caulked to bond the housing 1 and the insulation porcelain 2 to form an integrated unit. A center electrode 3 is fittingly engaged in one end (or a lower end) of a throughhole (or hollow portion) 2a of the insulation porcelain 2.

30 The center electrode 3 is made in the form of a cylinder composed of a copper core surrounded by a heat resistant Ni shell. The center electrode 3 has a front end 3a exposed from the lower end of the insulation porcelain 2.

35 A ground electrode 4 extends upward from an end surface of the housing 1 and bows right so that the leading end thereof faces the front end 3a of the center

electrode 3. The ground electrode 4 is also made of a Ni alloy. Noble metal chips 5 and 6 are bonded to the front end 3a of the center electrode 3 and the discharging spot of the ground electrode 4 facing the front end 3a by
5 laser or resistance welding to form a spark gap 7 :
therebetween.

A center pin 8 and a terminal 9 are electrically connected to an upper end of the center electrode 3 as is well known in the art. The terminal 9 is to be connected
10 to an external circuit for applying a high voltage to generate a spark. A seal gasket 10 surrounds the casing 1 at the upper end of the thread 1a for mounting the plug on an engine.

The most important feature of the present invention resides in the alloy material of the noble metal chips 5 and 6, i.e., at least one of the chips 5 and 6 is
15 composed of an Ir-Rh alloy based on Ir (iridium), which has a high melting point and good consumption resistance, and containing Rh (rhodium) for preventing Ir from
20 volatilizing at high temperatures.

The present inventors have conducted an experiment to determine the noble metal chips 5 and 6 composed of the Ir-Rh alloy. The results are shown in Fig. 3.

Figure 3 shows the chip consumption in terms of the increment of the spark gap 7 during an engine endurance
25 test for an Ir chip and Ir-based alloy chips containing any noble metal of the platinum families, i.e., Pt, Pd, or Rh.

The test was carried in a four-cycle, four-cylinder,
30 2000 cc engine continuously operated at a full load of 4000 rpm, during which the spark gap increment was measured. The tested plugs had a center electrode 3 and a ground electrode 4 with the noble metal chips made of the same metal or alloy.

35 The center electrodes 3 had noble metal chips 5 made of different materials of 100 wt% Ir, an Ir-10 wt% Pd alloy, an Ir-10 wt% Pt alloy, and an Ir-10 wt% Rh alloy.

The chips 5 had a unified dimension of an outer diameter A of 1.0 mm and a height B of 1.5 mm.

5 The ground electrodes 4 had noble metal chips 6 made of the same materials as those of the counterpart center electrodes 3 and had a unified dimension of an outer diameter C of 1.0 mm and a height D of 0.5 mm.

10 As can be seen from Fig. 3, the test result shows that the addition of another noble element in Ir reduces the chip consumption and improves the consumption resistance and the lifetime. The improvement is most evident when Rh is added in Ir.

15 The material of 100 wt% Ir only provided a small improvement, because Ir forms a volatile IrO_3 oxide at temperatures near 1000°C causing a large consumption even though Ir has a high melting point.

20 Then, the addition of any of less volatilizable noble metals of Pd, Pt, and Rh prevents the volatilization consumption of Ir. The addition of Rh is most effective, mostly because Rh has a melting point of 1960°C , which is higher than those of Pt (1769°C) and Pd (1552°C).

25 Although, in the tested plugs, the noble metal chip 5 of the center electrode 3 had a dimension of an outer diameter A of 1.0 mm and a height B of 1.5 mm, the noble metal chip 5 of the center electrode 3 preferably has an outer diameter of from 0.5 mm to 2.0 mm. When the chip 5 has an outer diameter A of less than 0.5 mm, the consumption resistance is greatly reduced and a long lifetime cannot be achieved. On the other hand, when the
30 noble metal chip 5 has an outer diameter A of more than 2.0 mm, the ignitability is reduced and the discharging voltage is increased, and accordingly, the improvement in the plug performance is reduced.

35 The chip height B of the noble metal chip 5 is preferably within the range of from 0.3 mm to 2.5 mm. The chip height B of the noble metal chip 5 must be

0.3 mm or more to ensure stable welding thereof with the center electrode 3. On the other hand, when the chip height B is more than 2.5 mm, the noble metal chip 5 will be easily broken.

5 Although, in the tested plugs, the noble metal chip 6 of the ground electrode 4 had a dimension of an outer diameter C of 1.0 mm and a height D of 0.5 mm, the noble metal chip 6 of the ground electrode 4 preferably has an outer diameter C of from 0.5 mm to 1.7 mm. When
10 the chip 6 has an outer diameter C of less than 0.5 mm, the consumption resistance is greatly reduced and a long lifetime cannot be achieved. On the other hand, when the noble metal chip 6 has an outer diameter C of more than
15 1.7 mm, the chip 6 cannot provide stable welding because the size is excessively large relative to that of the ground electrode 4.

 The chip height D of the noble metal chip 6 is preferably within the range of from 0.3 mm to 1.0 mm. The chip height D of the noble metal chip 6 must be
20 0.3 mm or more to ensure stable welding thereof with the ground electrode 4. On the other hand, when the chip height D is more than 1.0 mm, the consumption of the chip 6 is greatly increased by a significant elevation of the chip temperature.

25 Based on the result that the addition of Rh in Ir increases the consumption resistance, a detailed study was conducted to estimate the consumption resistance of the Ir-Rh alloy. Fourteen Ir-Rh chips having different contents of Rh were tested to determine the consumption
30 resistance under the same conditions as used in the above-described test including the chip dimensions. The results are summarized in Table 1, in which the chip consumption is shown in terms of the gap increment after a 400-hour engine endurance test.

35 It can be seen from Table 1 that, when the Ir-Rh alloy contains Rh in an amount of 1.0 wt% or more, the chip consumption is 0.18 mm or less, indicating a

remarkable improvement in the consumption resistance. Because the noble metal chip 5 or 6 becomes easier to break at the edge as the Rh content is increased, the Rh content of the noble metal chip 5 or 6 of a spark plug must not be more than 60 wt%.

The consumption resistance is further improved, if an oxide of a group 3A element (such as Y_2O_3) or an oxide of a group 4A element (such as ZrO_2) of the periodic table is added in the Ir-Rh alloy, as can be also seen from Table 1, particularly the data for Chips 11 to 14.

The Ir-Rh alloy of the present invention may further contain one or more elements of the platinum families other than Rh, i.e., Pt and Pd, and/or one or more heat resistant metals such as Ni, in an amount causing no substantial reduction in the advantageous effect provided by the combination of Ir and Rh, as can be seen from Table 1, particularly Chips 8 to 10.

Rh may be added in Ir by either process of melting or sintering. The present inventors confirmed that both processes provide substantially the same improvement in the consumption resistance.

Although spark plugs having noble metal chips 5 and 6 in both the center electrode 3 and the ground electrode 4 were discussed above, the present invention can be also advantageously applied to spark plugs in which only the center electrode 3 has a noble metal chip 5 and the ground electrode 4 does not have a noble metal chip 6.

Table 1

Chip No.	Composition (wt%)	Consumption (mm)
1	100 Ir	0.30
2	Ir-0.3Rh	0.27
3	Ir-1.0Rh	0.18
4	Ir-3.0Rh	0.13
5	Ir-10Rh	0.10
6	Ir-30Rh	0.12
7	Ir-60Rh	0.15
8	Ir-10Rh-10Pt	0.15
9	Ir-10Rh-0.5Ni	0.11
10	Ir-10Rh-5.0Ni	0.19
11	Ir-10Rh-0.5Y ₂ O ₃	0.09
12	Ir-10Rh-5.0Y ₂ O ₃	0.08
13	Ir-10Rh-0.5ZrO ₂	0.09
14	Ir-10Rh-5.0ZrO ₂	0.08

Ir-Rh alloy contains Rh in an amount of from 3 wt% to 30 wt%.

20 3. A spark plug according to claims 1 or 2, wherein the Ir-Rh alloy further contains an oxide of an element of the group 3A or 4A of the periodic table in an amount of from 0.5 wt% to 5 wt%.

 4. A spark plug according to claim 3, wherein the
25 oxide of the element of the group 3A consists of Y_2O_3 .

 5. A spark plug according to claim 3, wherein the oxide of the element of the group 4A consists of ZrO_2 .

 6. A spark plug according to any one of claims 1 to 5, wherein the center electrode has the noble metal
30 chip having an outer diameter A and a height B which are within the range defined by the following formulae:

$$0.5 \text{ mm} \leq A \leq 2.0 \text{ mm, and}$$

$$0.3 \text{ mm} \leq B \leq 2.5 \text{ mm.}$$

 7. A spark plug according to any one of claims 1
35 to 6, wherein the ground electrode has the noble metal chip having an outer diameter C and a height D which are

within the range defined by the following formulae:

$0.5 \text{ mm} \leq C \leq 1.7 \text{ mm}$, and

$0.3 \text{ mm} \leq D \leq 1.0 \text{ mm}$.

5 8. A spark plug according to any one of claims 1 to 7, wherein the center electrode has a shell portion composed of a Ni alloy and has the noble metal chip bonded to the discharging spot of the front end thereof by laser welding or resistance welding.

10 9. A spark plug according to any one of claims 1 to 7, wherein the ground electrode has a shell portion composed of a Ni alloy and has the noble metal chip bonded to the discharging spot of the front end thereof by laser welding or resistance welding.

15 10. A noble metal chip for a spark plug of an internal combustion engine, the chip being suitably bonded to at least one of a center electrode and a ground electrode of the spark plug at a discharging spot of a front end thereof, wherein:

20 the noble metal consists of an Ir-Rh alloy containing Rh in an amount of from 1 wt% to 60 wt%.

11. A noble metal chip according to claim 10, wherein the Ir-Rh alloy further contains an oxide of an element of the group 3A or 4A of the periodic table in an amount of from 0.5 wt% to 5 wt%.

12. A spark plug substantially as hereindescribed with reference to the accompanying drawings.

13. A noble metal chip for a spark plug, the chip being substantially as described herein with reference to the accompanying drawings.



Application No: GB 9612834.3
Claims searched: 1 to 13

Examiner: John Twin
Date of search: 1 August 1996

Patents Act 1977
Search Report under Section 17

Databases searched:

UK Patent Office collections, including GB, EP, WO & US patent specifications, in:

UK CI (Ed.O): F1B (BCAD); C7A

Int CI (Ed.6): C22C 5/04; H01T 13/39

Other: Online: EDOC, WPI

Documents considered to be relevant:

Category	Identity of document and relevant passage	Relevant to claims
X	GB 479540 (Powell et al.) - see eg page 2, lines 62-80	1,2,10 at least
X	JP 61044141 A (NGK) - see eg WPI abstract, Acc. no.86-098307/15 - see eg first sentence of abstract	1,2,10 at least

X Document indicating lack of novelty or inventive step
Y Document indicating lack of inventive step if combined with one or more other documents of same category.
& Member of the same patent family

A Document indicating technological background and/or state of the art.
P Document published on or after the declared priority date but before the filing date of this invention.
E Patent document published on or after, but with priority date earlier than, the filing date of this application.